

P R O D U C T D A T A S H E E T**P H Y S I C A L C H A R A C T E R I S T I C S**

Ruvitex Adhesive Contact 'a'	
Appearance	Amber
Base	Nitrile
Solids	Approximately 27%
Viscosity	Approximately 1500 cps
Tack life	1–5 mins
Coverage	Approximately 3 sqm per litre depending on temperature.
Cleaner	Solvent 3 or 4
Flash point	See MSDS
Shelf life (under recommended storage conditions)	12 months @ 6–25C
Any other essential data	Observe storage conditions carefully

Ruvitex Adhesive Contact 'a' two way stick or contact adhesive suitable for bonding Ruvitex PVC membranes to a variety of substrates including tissue faced polyurethane insulation, plywood/OSB and timber. **Ruvitex Adhesive Contact 'a'** is generally used to bonded membranes to vertical surfaces such as up-stand details etc.

Application

Apply adhesive to both surfaces. Allow to dry for 5 minutes or until the adhesive film no longer transfers to the fingers. Join the two surfaces taking care not to trap air and use as much pressure as possible in consolidating the bond.

**Assembly**

Bring the two dry coated surfaces into contact and press together over the whole bond area. Hand pressure is normally sufficient, but when applicable a hand roller may be used. Sustained pressure is unnecessary.

In conditions of high humidity a 'bloom' may form on the surface. This reduces tack and inhibits coalescence. It is not advisable to apply and use the adhesive under these conditions.

The adhesive and roof temperature during application **must not be below 6°C or in excess of 25°C** as the performance of the adhesive will be **dramatically reduced**.

**RUVITEX UK LTD**

74 Queens Road
Hersham
Surrey
KT12 5LW

Phone: +44 (0) 1484 429 397
Mobile: + 44 (0) 7939 353 595
Fax: +44 (0) 872 115 3075
E-mail: info@ruvitex.co.uk
Web: www.ruvitex.co.uk